



You are about to apply the best looking and most durable finish on the market: Better than Oil, Water, Moisture Cure or any other technology!

CLEAR GYM FINISH

POLOKEY

PROFESSIONAL PROTECTION FOR HARDWOOD FLOORS™

FOR SCREEN & RECOATS



SPECIFICATIONS

VOC.....	<275 g/L
Solids.....	61%
Flash Point.....	>102
Solvents	Alcohol
Pot Life	2-4 hrs. @ Rm Temp
Coverage.....	400 sf/g
Sheen.....	Gloss [In Stock]
All Other Sheens	[Custom Made]
Color.....	Crystal Clear
Available In	5g Containers

FEATURES

Low VOC less than 275
Not flammable: Flash point greater than 102 F°
Easy to apply; low viscosity; great flow & leveling
Clear formula will never amber paint or graphics
Extremely scratch and scuff resistant; better than any water or oil based product, including UV cured finishes.
No waiting! Play on the floor the day after coating
Open time 20-30 minutes wet edge
Years before refinish is necessary
No side bonding
Please refer to Product Application sheet for Instructions

Toughest PoloPlaz Finish Ever Made

PoloKey is formulated to withstand even the most demanding gym floor conditions. At 61% solids and low viscosity, PoloKey is ideal for recoats and new installations or resands. Its crystal clear film will never amber game lines or logos so your white lines stay white.

When summer schedules run tight, choose PoloKey for a quick turnaround. Resume play in just 24-36 hours after coating is dried without the worry of scuffing or scratching the floor. PoloKey is the toughest product in the PoloPlaz lineup so your floors continue to look great even after a year of heavy play. With a VOC limit below 275 g/L, PoloKey is the perfect choice for LEED projects and discerning architects.

TOLL FREE (800) 421-7319 | OFFICE (501) 985-1172 | FAX (501) 985-1359 | 1 Paradise Park Road, Jacksonville, AR 72076

MADE IN THE USA  POLOPLAZ.COM

PROFESSIONAL PROTECTION FOR HARDWOOD FLOORS™

FOR SCREEN & RECOATS PRODUCT APPLICATION



Temperature of materials should be 70-80° F.

Step 1: Once floor is properly abraded and free of contamination, tack with PK cleaner and allow to dry thoroughly (approx. 20-30 minutes) before coating with Polo Key. Final abrasion with 180 grit (i.e. 3M™ hook & loop discs with SPP Pad or equivalent) for Polo Key (as it is a clear finish).

Wear Personal Protection.

Measure the Floor:

Proper coverage is 400 sq ft. per gallon. To Maintain proper rate of coverage: Light weight T-Bar application is preferred, but one can use a roller. Use a premium non shedding 3/16" or 1/4" inch nap cover. Roll finish out of a plastic tray to prevent puddles and gloss variance from puddles. Never use a metal pan!

Step 2: Remove lid from container (Part A) and mix thoroughly prior to catalyzing; Add Part B while stirring vigorously with a wooden stir stick. Never use a metal paint paddle. Product will not cure unless thoroughly mixed. Never use an out of date catalyst.

WARNING: *If catalyst (Part B) is not added and mixed thoroughly the material will remain wet and never cure!!! After catalyzing a container, identify with a ribbon of tape on the handle. It is easy to lose track of which are catalyzed.*

Step 3: Apply product. The wet edge of the product is about 20-30 minutes at 70° F. At 90° F, the wet edge is REDUCED. Cooler temps produce longer wet edge times. Change applicators or rollers EVERY 45-60 MINUTES, as the roller begins to breakdown. Clean up with Denatured Alcohol.

Step 4: After coating, turn on air conditioning or heat for air flow (open windows slightly if possible) to accelerate cure and to remove any odors present. At 70° F, the material will be cured 24 hours after the application is dry and ready for move in. Lower temps require longer cure.

Polo Key is Clear & Never Ambers!!

Use only PoloPlaz Hardwood Floor Cleaner. The more you maintain your floor, the longer it will last!
Thank you for using Prime Advantage!! Please send pictures to sales@poloplaz.com!!